	Hits	Search Text	DBs
1	1387	(428/198).CCLS.	US- PGPUB; USPAT
2	798	(428/114).CCLS.	US- PGPUB; USPAT
3	1942	(428/131).CCLS.	US- PGPUB; USPAT
4	1664	(428/137).CCLS.	US- PGPUB; USPAT
5	1522	(428/138).CCLS.	US- PGPUB; USPAT
6	202	(428/170).CCLS.	US- PGPUB; USPAT
7	339	(428/171).CCLS.	US- PGPUB; USPAT
8	1871	(428/172).CCLS.	US- PGPUB; USPAT
9	574	(428/152).CCLS.	US- PGPUB; USPAT
10	2018	(428/156).CCLS.	US- PGPUB; USPAT
11	143	(442/352).CCLS.	US- PGPUB; USPAT
12	216	(442/328).CCLS.	US- PGPUB; USPAT
13	59	(442/353).CCLS.	US- PGPUB; USPAT
14	16	(442/358).CCLS.	US- PGPUB; USPAT
15	59	(442/359).CCLS.	US- PGPUB; USPAT

Class Made Manual Manua

	Hits	Search Text	DBs
16	28	(442/360).CCLS.	US- PGPUB; USPAT
17	441	(442/361).CCLS.	US- PGPUB; USPAT
18	588	(442/381).CCLS.	US- PGPUB; USPAT
19	1451	(604/378).CCLS.	US- PGPUB; USPAT
20	277	(604/380).CCLS.	US- PGPUB; USPAT
21	286	(604/383).CCLS.	US- PGPUB; USPAT
22	258	(604/385.101).CCLS.	US- PGPUB; USPAT
23	1072	(604/385.01).CCLS.	US- PGPUB; USPAT

Oglass & Sand Minds And Break

	Hits	Search Text	DBs
1	0	pne same heat near2 shrink\$8	US- PGPUB; USPAT
2	226	pne	US- PGPUB; USPAT
3	529	polyethylene near7 polypropylene near7 random near7 copolymer	US- PGPUB; USPAT
4	0	polyethylene near7 polypropylene near7 random near7 copolymer same heat near5 shrink\$8	US- PGPUB; USPAT
5	29	mear7 conclimer and heat hearh	US- PGPUB; USPAT
6	71	polyethylene near7 polypropylene near7 random near7 copolymer same fiber	US- PGPUB; USPAT
7	1	"5229191".pn.	US- PGPUB; USPAT

Colors 802 East Bas Very Search Manual Manual Manual Manual